



Consolidated Alloys

A Division of C.A. Group Australasia Pty. Limited inc in Vic.
ABN 83 005 084 097

www.cagroup.com.au

JUNE 2008

SILVER

PRODUCT DESCRIPTION Soft, white, lustrous transition metal supplied in granular form to 99.99% purity. Can be supplied as small ingots.

APPLICATIONS Primarily used in the electronics industry. Also used as an alloy in solder and brazing alloys, dentistry, photographic film and silver nitrate.

SPECIFICATION

- **Purity:** 99.99% pure
- **Melting Point:** 962°C
- **Specific Gravity:** 10.49gm per cc
- **Form:** Granules
- **Chemical Symbol:** Ag

THIS DATA SHEET IS OFFERED SOLELY FOR YOUR INFORMATION, CONSIDERATION AND INVESTIGATION. CONSOLIDATED ALLOYS PROVIDES NO WARRANTIES, EITHER EXPRESSED OR IMPLIED AND ASSUMES NO RESPONSIBILITY FOR THE ACCURACY OR COMPLETENESS OF THE DATA CONTAINED HEREIN. MATERIAL USE BEYOND THE CONTROL OF SUPPLIER

MELBOURNE (Head Office):
32 Industrial Avenue.
Thomastown, Vic. 3074
Telephone: (03) 9359 5811
Facsimile: (03) 9359 4076

SYDNEY:
5 Coates Place,
Wetherill Park, N.S.W. 2164
Telephone: (02) 9756 4011
Facsimile: (02) 9756 4074

BRISBANE:
Chrome Street,
Salisbury Nth, Qld. 4107
Telephone: (07) 3277 2977
Facsimile: (07) 3875 1994

PERTH:
1/19 Dowd Street,
Welshpool, W.A. 6106
Telephone: (08) 9353 4818
Facsimile: (08) 9353 4814

ADELAIDE:
Solder-Tech Pty. Ltd.
St Marys, S.A. 5042
Telephone: (08) 8276 8566
Facsimile: (08) 8276 9849

TASMANIA:
Wholesale Products Pty. Ltd.
Glenorchy, TAS. 7010
Telephone: (03) 6273 3455
Facsimile: (03) 6273 1901